
Single-Sided PVC Foam Tape (SBV, SGV, SWV)

Product Description

Sealprem foam sealants are manufactured from expanded PVC in a range of densities. They are essentially closed cell structures coated with a pressure sensitive acrylic adhesive and require 33% compression to create an air seal. They are available in rolls, logs and gasket form.

Features

- Slit to order – many widths and thicknesses available
- Flexible and conformable
- Clean, economical and easy to use
- SBV20 – low density, black
- SBV25 – medium density, black
- SGV25 – medium density, grey
- SBV50 – high density, black
- SGV50 – high density, grey

Typical Applications

- Roofing and cladding seals
- Coldroom panels and cold bridging
- Sealing partition walls
- Heating and ventilation
- Rooflights, access doors and gutter joints
- Profiled sheeting
- Prefabricated tanks

Please note: The above technical information is given as a guide and is based on recent test data obtained under laboratory conditions. Materials should be fully tested by the end user to establish suitability of the product for the intended application. March 2024

Premier Sealant Systems Ltd.

T 01724 864 100 | E sales@sealprem.com | www.sealprem.com

Mercia Way, Foxhills Industrial Park, Scunthorpe, DN15 8RE

Registered Office: Mercia Way, Foxhills Industrial Park, Scunthorpe, DN15 8RE | Registered in Cardiff No. 3000843

	20 Series	25 Series	50 Series
Adhesive	Acrylic	Acrylic	Acrylic
Colours	Black/White	Black/Grey	Black/Grey
Thicknesses (mm)	Black: 3, 4.5, 6 White: 3, 6	Black: 1.5, 3, 4.5, 6, 7.5, 9, 10.5, 12 Grey: 1.5, 3, 4.5, 6	Black: 1.5, 3, 4.5, 6 Grey: 0.8, 1.5, 2.5, 3, 4.5, 6
Density (kg/m ³)	115	130	220
Shore Hardness (00 Scale)	30	35	50
Force to Compress (Ncm ⁻²)	2.7	3.2	6.1
Tensile strength (N/cm ²)	25	30	66
Elongation at Break (%)	>160	>155	>180
Peel Adhesion (N/25mm)	5	5	5
Service temperature	-30°C to +70°C	-30°C to +70°C	-30°C to +70°C
Application temperature	+10°C to +40°C	+10°C to +40°C	+10°C to +40°C
UV Resistance	Excellent	Excellent	Excellent
Fungi resistance	Excellent	Excellent	Excellent
Weather resistance	Excellent	Excellent	Excellent
Shelf life	2 years	2 years	2 years

Please note: The above technical information is given as a guide and is based on recent test data obtained under laboratory conditions. Materials should be fully tested by the end user to establish suitability of the product for the intended application. March 2024

Premier Sealant Systems Ltd.

T 01724 864 100 | E sales@sealprem.com | www.sealprem.com

Mercia Way, Foxhills Industrial Park, Scunthorpe, DN15 8RE

Registered Office: Mercia Way, Foxhills Industrial Park, Scunthorpe, DN15 8RE | Registered in Cardiff No. 3000843